

URECOAT TOP

This specification applies to the urethane flooring construction shown in the drawing. It is a paint mainly composed of polyurethane resin. Samhwa paint or equivalent products should be submitted in advance and approved by the supervisor.

1. Special Feature

Urecoat Top, mainly composed of aliphatic urethane resin, is an elastic floor coating that provides non-slip quality that is suitable for floor decorating as well as coating for architectural surfaces. It is a soft touch, anti-abrasion coating with superior adhesion for a beautiful finish.

2. Usage

Top coat for urethane systems of sports facilities & floorings

3. Application

Surface Preparation	<ol style="list-style-type: none"> Surface preparation <ul style="list-style-type: none"> The surface to be coated should be sufficiently dry. (Relative humidity 80% or less at 25 °C, sufficient curing for 28 days or more) All surfaces must be free of rust, dust, grease, oil, moisture or other contaminants. Minimum concrete strength need more than 160 kgf/㎠. In case of high strength concrete (260 kgf / ㎠ or more), it is necessary to perform surface treatment by blasting method because bad adhesion may occur during the treatment of grinding. Environmental conditions <ul style="list-style-type: none"> Air temperature: 10 to 35°C range. Relative humidity: up to 80%. <p>*note: To prevent moisture condensation during application, surface temperature must be at least 3°C above the dew point. In confined spaces, ventilation is required during application and drying.</p> Application Equipment <ul style="list-style-type: none"> Roller, Brush, Air Spray 																																							
Application System	Primer : URECOAT PRIMER Top Coat : URECOAT TOP COATING																																							
Coverage	<table border="1"> <thead> <tr> <th>Coating order</th> <th>Product name</th> <th>Standard number</th> <th>Coating times</th> <th>Dry film thickness</th> <th>Theoretical consumption</th> <th>Actual consumption</th> <th>Remark</th> </tr> </thead> <tbody> <tr> <td>Primer</td> <td>URECOAT PRIMER</td> <td></td> <td>1</td> <td>50</td> <td>0.138L/m²</td> <td></td> <td></td> </tr> <tr> <td>Top Coat</td> <td>URECOAT TOP COATING</td> <td></td> <td>3</td> <td>150</td> <td>0.294L/m²</td> <td></td> <td></td> </tr> <tr> <td>TOTAL</td> <td></td> <td></td> <td>4</td> <td>200</td> <td></td> <td></td> <td></td> </tr> </tbody> </table> <p>* Practical Coverage can be increased or decreased followed by working condition, work method, and so on. * VAT not included * Separation of construction cost</p>								Coating order	Product name	Standard number	Coating times	Dry film thickness	Theoretical consumption	Actual consumption	Remark	Primer	URECOAT PRIMER		1	50	0.138L/m ²			Top Coat	URECOAT TOP COATING		3	150	0.294L/m ²			TOTAL			4	200			
Coating order	Product name	Standard number	Coating times	Dry film thickness	Theoretical consumption	Actual consumption	Remark																																	
Primer	URECOAT PRIMER		1	50	0.138L/m ²																																			
Top Coat	URECOAT TOP COATING		3	150	0.294L/m ²																																			
TOTAL			4	200																																				
Application Procedure	<ol style="list-style-type: none"> Primer <ul style="list-style-type: none"> After finishing the treatment, apply Urecoat Primer 50μm once with roller or brush. It is used without dilution and it is applied so that it penetrates sufficiently on the surface. If the undercoat is thick on the surface of the substrate, the contact area between the substrate and the center will be reduced and the adhesion will be poor. The untreated parts should be applied without leaving them because of the possibility of air bubbles in the middle coating. For the part where more than 2 days have elapsed since the painting, add a thin coating to the layer to reinforce the interlayer adhesion. Use the material within pot life. Top Coat <ul style="list-style-type: none"> Within 2 days after the completion of the intermediate coating, mix the base of Urecoat Top Coating and the hardener in a volume ratio of 6.3 : 1 and apply once 50 μm. Mix only the amount to be used within the pot life and dilute urethane 1000 thinner by 5%. 																																							
Caution	<ol style="list-style-type: none"> Avoid contact with eyes and repeated contact with skin. Keep away from heat and open flame. Keep adequate ventilation during application. Avoid breathing of vapors or spray mist. After the painting work, please wash exposed skin thoroughly. Keep the container closed when not in use. Store in the area beyond children's reach. Do not mix this product with other paints. Avoid applying paint on rainy days, high humidity (over 80%), low temperature (below 5 °C) and high temperature (over 40 °C surface temperature). Store the product in a dry, cool place at room temperature (5 ~ 35 °C) away from fire and direct sunlight. Keep container tightly 																																							

closed with the injection port facing up.

11. Alcohol-Containing thinner(Epoxy thinner) never use. When use it, Paints doesn't dry.

12. Since this product is a chemical product, it may deteriorate during long-term storage. Please use it within the validity period.
Please use the product after confirming it with the consumer counseling room.
